

Materiály a rozsahy měření pro přenosné digit. tvrdoměry

Materiál	Stupnice tvrdosti	D/DC	D+15	C	DL	G
		LD:170-900	LD+15:330-900	LC: 350-950	LDL: 560-950	LG: 200-750
Ocel a litá ocel	HRC	20 – 68,4	19,3 – 67,9	20 – 69,5	20,6 – 68,2	
	HRB	38,4 – 99,8			37 – 99,9	47,7 – 99,9
	HRA					
	HB	81 – 654	80 – 638	80 – 683	81 – 646	90 – 646
	HV	81 – 955	80 – 937	80 – 996	80 – 950	
	HS	32,5 – 99,5	33,3 – 99,3	31,8 – 102,1	30,6 – 96,8	
Nerez	HRB	46,5 – 101,7				
	HB	85 – 655				
	HV	85 – 802				
Studená nástroj. ocel	HRC	20,4 – 67,1	19,8 – 68,2	20,7 – 68,2		
	HV	80 – 898	80 – 935	100 – 941		
Šedá litina	HRC					
	HB	93 – 334				92 – 326
	HV					
Slitina hliníku	HB	19 – 164		23 – 210		32 – 168
	HRB	23,8 – 84,6		22,7 – 85,0		23,8 – 85,5
Mosaz	HB	40 – 173				
	HRB	13,5 – 95,3				
Bronz	HB	60 – 290				
Měď	HB	45 – 315				

